

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 0 842 756 A1**

(12)

## EUROPEAN PATENT APPLICATION

(43) Date of publication:  
20.05.1998 Bulletin 1998/21

(51) Int. Cl.<sup>6</sup>: B29C 65/08, A47K 10/02

(21) Application number: 97203237.9

(22) Date of filing: 16.10.1997

(84) Designated Contracting States:  
AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC  
NL PT SE  
Designated Extension States:  
AL LT LV RO SI

(30) Priority: 08.11.1996 US 745350


(71) Applicant:  
MILLIKEN RESEARCH CORPORATION  
Spartanburg South Carolina 29304 (US)

(72) Inventor:  
Rockwell, James Nelson, Jr.  
La Grange, GA 30240 (US)

(74) Representative:  
Hanna, Peter William Derek et al  
Tomkins & Co.,  
5 Dartmouth Road  
Dublin 6 (IE)

### (54) Ultrasonically spliced roll towel

(57) A roll towel (10) for use in the drying of hands in a lavatory setting is provided. The roll towel includes at least two segments of textile material which include at least 60 percent polyester fiber. The two segments of textile material are spliced together by an ultrasonically formed seam (16). The seam is preferably made up of a series of bonding points (18) offset from one another by nonbonded segments.



**FIG. -1-**

Ref. #15  
KCC 4809  
Mark J. Beitz, et al.  
10/039,238

**EP 0 842 756 A1**

**Description****FIELD OF THE INVENTION**

5 This invention relates generally to hand drying roll towels and more particularly to polyester roll towels including an ultrasonically applied splice between segments of such roll towels.

**BACKGROUND OF THE INVENTION**

10 Hand drying roll towels for use in public lavatories are well known. Such roll towels typically are mounted in a wall hanging cabinet having supply and take-up rolls such that the user can pull down a clean, unused segment of the towel from the supply roll with the previously used segment of the towel being conveyed back to the take-up roll. In the past, such towels have typically been formed primarily of cotton so as to provide the user with the absorbency and texture benefits of such a product.

15 Roll towels are typically formed from woven fabric structures as are well known to those of skill in the art. The fabric which is formed is thereafter typically sealed at the edges by sewing and then shipped in roll form to rental laundries. In practice, these laundries install clean towels and reclaim soiled towels for cleaning and reuse. The length of such fabric segments is generally in the range of about 21 meters.

20 As will be appreciated, at times it is necessary to splice segments of material together to form a complete length for use in a roll towel application. More significantly, once the roll towel is in actual use, it may be necessary to cut out damaged or stained portions of the towels and splice the remainder back together. This is particularly true since the towels undergo multiple uses in between which they are washed and inspected. In prior practice, such splicing was generally accomplished by means of standard sewn seams traversing the width of the fabric. While such sewn seams are extremely strong, they are generally considered to be aesthetically displeasing since the towel tends to take on a dog-bone profile in the vicinity of the seam. This is particularly true once a number of sections of the roll towel material have been cut and spliced back together.

25 In light of the above, it would be advantageous to have a roll towel wherein a strong, spliced seam may be formed by means other than a standard sewing procedure. The present invention provides such a roll towel and method for forming a splice therein in accordance with the claims which follow. Preferably the spliced seam is formed by a patterned ultrasonic bond disposed across the width of the roll towel.

**BRIEF DESCRIPTION OF THE DRAWINGS**

FIG. 1 is a plan view of a roll towel according to the present invention.

35 FIG. 2 is a perspective view of an ultrasonic seam-forming arrangement for use in accordance with the process of the present invention.

FIG. 3 is an ultrasonic horn for use in forming a seam across a roll towel in accordance with the process of present invention.

40 FIG. 4 is an ultrasonic horn for use in forming a seam across a roll towel in accordance with the process of the present invention.

While the invention has been illustrated and will be described in connection with certain preferred embodiments and procedures, it is, of course, to be appreciated that there is no intention to limit the invention to such particularly illustrated and described embodiments and procedures.

**DESCRIPTION OF THE PREFERRED EMBODIMENTS**

45 Turning now to the figures, in FIG. 1 there is shown a roll towel 10 according to the present invention. In the illustrated and potentially preferred embodiment, the roll towel 10 includes an ultrasonically bonded, boundary edge 12 disposed on either side of an intermediate textile surface 14. In the preferred embodiment, the roll towel 10 is formed of polyester or cotton/polyester fiber which preferably includes at least 60 percent polyester so as to promote a strong, ultrasonic bond between the fibers. In the most preferred practice, 100 percent polyester is utilized.

55 As illustrated, the ultrasonically bonded, boundary edges 12 preferably have a discontinuous brick-like pattern formed therein by a patterned backing wheel operating adjacent to an ultrasonic horn with fabric disposed therebetween. Such a discontinuous brick-like pattern is believed to provide exceptional flexibility which in turn promotes the operability of the product on the supply and take-up rolls of a cabinet structure in a public lavatory.

As illustrated, the roll towel 10 may also include one or more ultrasonically formed splices 16 disposed across the width of the roll towel structure 10 thereby joining overlapped segments of the roll towel 10 together forming a longer overall structure. The ultrasonically formed splice 16 preferably includes a discontinuous (i.e. nonsolid) seam having a

pattern of bonding points 18 offset from one another by segments within the boundaries of the seam which are not ultrasonically bonded. The bonding points 18 preferably have both longitudinal and latitudinal stress carrying components. In practice, clear tape may be used to aid in alignment of such splices.

By way of example only, and not limitation, in the illustrated, and potentially preferred embodiment, the bonding points 18 are of an elongated "S" shaped configuration. It is believed that such a configuration carries latitudinal loads along the top and bottom portions of the "S" while carrying longitudinal stresses along the elongated middle portion.

The ultrasonically formed splices 16 are preferably put in place by an ultrasonic bonding apparatus 20 as illustrated in FIG. 2. One potentially preferred ultrasonic bonding apparatus is the FS90 ultrasonic welder with a 910 BC series power supply available from Branson Ultrasonics Corporation having a place of business in Danbury, Connecticut, USA. As illustrated, the ultrasonic bonding apparatus preferably includes an actuation unit 22, an ultrasonic horn 24, and a bonding stand 26 for holding the roll towel 10 during the actual bonding operation. The bonding stand 26 also preferably includes a patterned wheel (not shown) which has a raised pattern of the bonding points 18 and which travels by rotation across the width of the roll towel 10 in opposed relation to the ultrasonic horn 24 with the fabric of the roll towel therebetween so as to form the splice 16. In the potentially preferred practice of the present invention, the ultrasonic horn 24 is a 25.4 mm (one inch) button horn (FIG. 4) which operates in conjunction with a 63.5 mm (2.5 inch) diameter pattern wheel available from Branson Ultrasonics. The actuation unit 22 has a power output of 1000 watts and generates an operating frequency of 20 KHz. In the potentially preferred practice, the splice 16 is formed at a rate of approximately 76.2 mm (3 inches) per minute. The splice which is formed preferably has a width of at least 9.5 mm (3/8 inches) so as to enhance the strength of the overall structure. It is believed that through proper formation of the splice 16, that strengths approaching those available with traditional sewn seams may be available. By way of illustration only and not limitation, the comparative strengths as measured by an Instron Tester using a 76.2 mm (three inch) seam segment are illustrated in Table 1.

TABLE I

Seam Type	Ultrasonic Solid Seam	Ultrasonic Brick Seam	Ultrasonic "S" Seam	Sewn Seam	No Seam
Breaking Strength - Newtons (Pounds Force)	151.2 (34)	253.6 (57)	333.6 (75)	409.2 (92)	1734.7 (390)

It is contemplated that a splice may also be formed by means of an elongated ultrasonic horn 30 (FIG. 3). In the use of such a horn, it is contemplated that a plunging type action may be utilized to bring the horn into adjacent relation to a permanently fixed pattern bar, thereby eliminating the need to move the horn and pattern wheel across the surface to be bonded and thus potentially speeding up the overall splicing process.

It is further contemplated that ultrasonic processes may also be utilized to form patterns on the intermediate woven surface 14 of the roll towel 10 using either the button-type horn 24 and patterned wheel or the elongated horn 30 and patterned backing bar. By way of example only, and not limitation, an icon or series of icons comprising a message 15 may be physically impressed upon the roll towel 10 so as to alert the users that replacement of the roll is required. Such a message would preferably be placed at the end of the roll so as to become visible when the feed roll is dissipated. In this way, the possibility of a soiled towel remaining in a position of use is substantially reduced. It is further contemplated that an ultrasonic edge bond could be established across the terminal ends 32 of the roll towel 10 so as to promote the seaming of the roll towels one to the other for conveyance through very large industrial laundry ranges without causing fraying when the stitches are removed once the laundering process is complete.

As will be appreciated, the present invention provides a roll towel structure having a number of benefits and advantages. While specific embodiments of the invention have been shown and described, it is to be understood that the invention is in no way limited thereto, since modifications may be made and other embodiments of the principles of this invention will no doubt occur to those of skill in the art. Therefore, it is contemplated by the appended claims to cover any such modifications or other embodiments as incorporate the features of the present invention within the scope thereof.

## Claims

1. A hand drying roll towel (10) of absorbent textile material for use in a lavatory setting, the roll towel comprising at least two segments of textile material joined by a transverse seam, characterized in that the textile material comprises at least 60 percent polyester, and in that the transverse seam comprises an ultrasonically formed seam (16) splicing together the said two segments wherein said ultrasonically formed seam comprises a series of bonding

points (18) offset one from the other by portions which are not ultrasonically bonded.

2. A hand drying roll towel (10) as in Claim 1, wherein said textile material consists essentially of polyester, preferably 100 percent polyester.
- 5 3. A hand drying roll towel (10) as in Claim 1, wherein said bonding points (18) have an elongated "S" shaped configuration.
- 10 4. A hand drying roll towel (10) as in Claim 1, further comprising at least one longitudinally extending ultrasonically bonded boundary edge (12).
5. A hand drying roll towel (10) as in Claim 1, further comprising one or more ultrasonically embossed message-conveying icons or indicia (15) disposed within said textile material.
- 15 6. A method for joining two segments of a hand drying roll towel (10) of absorbent textile material by a transverse seam, characterized by providing a textile material comprising at least 60 percent polyester, splicing together the said two segments by forming an ultrasonically bonded seam (16) comprising a series of bonding points (18) offset one from the other by portions which are not ultrasonically bonded.

20

25

30

35

40

45

50

55




FIG. -1-




FIG. -2-




FIG. -3-




FIG. -4-




FIG. -2-




FIG. -3-




FIG. -4-



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 97 20 3237

DOCUMENTS CONSIDERED TO BE RELEVANT					
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)		
Y	US 4 938 817 A (LANGLEY JOHN D) * claim 2; figures 1,2 *	1-6	B29C65/08 A47K10/02		
Y	US 5 232 529 A (MIYAKE TAKAO) * column 4, line 57 - line 61; claim 2 *	1,5,6			
Y	US 5 229 181 A (DAIBER HERMANN ET AL) * column 1, line 44 - line 48 * * column 2, line 3 - line 7 *	1,2,6			
Y	US 3 852 144 A (PARRY F) * column 1, line 47 - line 51 * * column 2, line 26 - line 29; figure 8 *	4			
Y	GB 1 249 857 A (SMITH AND NEPHEW PLASTICS) * claims 1,4 *	3			
Y	PATENT ABSTRACTS OF JAPAN vol. 013, no. 400 (M-867), 6 September 1989 & JP 01 145122 A (MITSUO FUJISAWA), 7 June 1989, * abstract; figures *	3			
Y	US 3 890 892 A (LOOSE GUENTER H ET AL) * abstract; figure 1 *	5			
Y	EP 0 340 334 A (DRESCHER GESCHAEFTSDRUCKE) * column 7, line 15 - line 22; figure 4C *	5			
A	PATENT ABSTRACTS OF JAPAN vol. 095, no. 010, 30 November 1995 & JP 07 178008 A (RYOICHI NISHIO), 18 July 1995, * abstract *	1,2	<table border="1"> <thead> <tr> <th>TECHNICAL FIELDS SEARCHED (Int.Cl.8)</th> </tr> </thead> <tbody> <tr> <td>B29C A47K B31F</td> </tr> </tbody> </table>	TECHNICAL FIELDS SEARCHED (Int.Cl.8)	B29C A47K B31F
TECHNICAL FIELDS SEARCHED (Int.Cl.8)					
B29C A47K B31F					
The present search report has been drawn up for all claims					
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>9 December 1997</b>	Examiner <b>Cordenier, J</b>		
<table border="0"> <tr> <td style="vertical-align: top;"> <b>CATEGORY OF CITED DOCUMENTS</b>  X : particularly relevant if taken alone  Y : particularly relevant if combined with another document of the same category  A : technological background  O : non-written disclosure  P : intermediate document </td> <td style="vertical-align: top;"> T : theory or principle underlying the invention  E : earlier patent document, but published on, or after the filing date  D : document cited in the application  L : document cited for other reasons    &amp; : member of the same patent family, corresponding document </td> </tr> </table>				<b>CATEGORY OF CITED DOCUMENTS</b> X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document	T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons  & : member of the same patent family, corresponding document
<b>CATEGORY OF CITED DOCUMENTS</b> X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document	T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons  & : member of the same patent family, corresponding document				

EPO FORM 1503 03 82 (P04/C01)





Eur p an Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 97 20 3237

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.8)
A	PATENT ABSTRACTS OF JAPAN vol. 015, no. 243 (C-0842), 21 June 1991 & JP 03 076849 A (KURARAY CO LTD), 2 April 1991, * abstract *	1	
A	US 3 222 239 A (H. DEANS) * column 5, line 20 - line 29 *	1,6	
A	US 5 464 488 A (SERVIN RANDALL F)	1,2,6	
A	DE 25 55 385 A (HEINRICH BECK KG) * page 5, paragraph 2; claims *	5	
A	EP 0 165 211 A (SILENT GLISS CASA SRL) * page 4, paragraph 3 * * page 7, paragraph 3 * * claims; figures *	3,4	
A	EP 0 170 629 A (SILENT GLISS CASA SRL) * page 3, line 10 - line 13 * * page 3, line 28 - line 11 * * page 5, line 23 - line 30 * * claim 3; figures *	1,3,4	
A	EP 0 689 530 A (HENKEL KGAA) * claim 2; figure 2 *	1	
A	FR 2 115 456 A (BRANSON INSTR) * page 1, line 10 - line 13 * * page 8, line 7 - line 17 *	1,3	
A	DE 12 94 175 B (FR. HESSER MASCHINENFABRIK AG) 11 September 1969 * figures 1-3 *		
The present search report has been drawn up for all claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>9 December 1997</b>	Examiner <b>Cordenier, J</b>
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

EPO FORM 1503 03.82 (P4/C01)